

Technical Data

NewColors

Tanning Tube OH N 21/25 Slim

UV-Code:^{**} 25-O-29/8,1


Article No.: 45006361

Dimensions: See drawing (not to scale)
 Socket: G5 / BiPin
 Reflector: without reflector, type O (reflector angle)

Electrical Data:
 Lamp Wattage nom.: 25 W
 Lamp Voltage: 65 V
 Lamp Current: 0,4 A
 Open-circuit voltage: 230 V / 50 Hz
 Ballast: Ballast 25 LP
 Starter: OH Suncare Standard 25 - 100 W
 Compensation: 4,5 µF(± 10% 250V)

Operation conditions:
 Cooling: Convection
 Burning Position: Horizontal
 Surrounding temperature: 25 °C ±1 °C

Irradiation Data:
 UVA Output: 6 W
 UVB Output: 2,4 %
 Sun erythema factor:^{*} 0,10
 Luminous colour: Standard blue
 (UVB:280-315 nm; UVA:315-400 nm)
 $E_{er \text{ total}}^*$: 29,1 mW/m² $E_{NMSC \text{ total}}^*$: 44,7 mW/m²
 $E_{er \leq 320}^*$: 24,3 mW/m² $E_{NMSC \leq 320} / E_{NMSC > 320}^*$: 8,1
 $E_{er > 320}^*$: 4,8 mW/m² E_{pi}^* : 5,8 W/m²



Lifetime:
 Standard lifetime: 800 h
 Reduction of UV-intensity: ≤ 30 % (315-400 nm) after 600 h
 Based on: 20 h - value

The data given are based on average data und has been determined by measurements made in the laborator under standard conditions. There could be minor deviations due to technical and/or physical reasons.

^{*} These irradiation data of a single tube have been measured in a distance of 25 cm.

^{**} Valid with 1h preageing process, 25 cm distance between tube surface and sensor, in thermal balance.

Sunbed intensity ^{*1} (315-400 nm)	UV- ^{*2} Device type	First ^{*3} tanning time	Tanning time in minutes ^{*3}			MED/h Skin type 3	UV- ^{*4} Index
			Skin type 2	Skin type 3	Skin type 4		
17 mW/cm ²	II	3 min	8 min	11 min	14 min	6	22
20 mW/cm ²	No	3 min	6 min	9 min	12 min	7	26
23 mW/cm ²	No	2 min	6 min	8 min	10 min	8	30
26 mW/cm ²	No	2 min	5 min	7 min	9 min	9	34

^{*1} UVA- Sunbed intensity, measured in heighth of the skin surface; ^{*2} Referring DIN EN 60335-2-27; ^{*3} Referring DIN 5050 Part 2; ^{*4} Referring B

Heraeus Noblelight GmbH
 Original Hanau SunCare
 Heraeusstraße 12-14
 D-63450 Hanau
 Phone: +49 6181 / 35-5092
 Fax.: +49 6181 / 35-5096
 E-Mail: suncare@heraeus.com
www.original-hanau-suncare.com



08.12.2005